



obomodulan® 210 light grey

Application

- Styling models
- Visualizing models
- Laminating models
- Thermoplastic deep drawing models
- Architectural models

Properties

- Fine cell structure
- Easy to machine
- Low dust

Description

- **obomodulan® 210** is a Polyurethane based material

Technical Data*

Density kg/m ³ (approx.)	200
Compressive Strength MPa (DIN EN ISO 604)	3
Bending strength MPa (DIN EN ISO 178)	3
Linear Thermal Expansion Co-efficient	$43 \times 10^{-6} \cdot K^{-1}$
Shore D (DIN 53505)	18 - 25
Deflection Temperature ISO 75	80 °C

*measured average values

Standard dimensions:

- 1500 x 500 x 100 mm
- 2000 x 500 x 100 / 150 / 200 mm
- 2000 x 1000 x 100 / 150 / 200 mm

Other dimensions, cuts, bonded blocks, rough pre-milling and block casts on request.

Boards, finished tools and models should be stored flat in dry conditions. The material should be acclimatized to 18 - 25° C prior to machining. Temperature variations should be kept as moderate as possible.

Status: 14.06.2016