



obomodulan® 750 turquoise

OBO-Werke GmbH

Am Bahnhof 5 · 31655 Stadthagen · Germany
Telefon (0 57 21) 78 01-0
Telefax (0 57 21) 7 78 55
www.obo-werke.de
info@obo-werke.de
USt-Id: DE171274404
St-Nr : 44/210/02193

Application

- laminating models
- master models
- vacuum forming moulds
- foundry patterns

Properties

- very fine surface structure
- easily machined

Description

- **obomodulan® 750 turquoise** is a Polyurethane based material

Technical Data*

Density approx. kg/m³	750
Compressive strength (DIN EN ISO 604) approx. MPa	30 – 35
Bending strength (DIN EN ISO 178) approx. MPa	25 – 40
Linear thermal expansion coefficient temperature from approx. 25 up to 70 °C (according to DIN 53752) 10⁻⁶ .K⁻¹	55 - 60 x 10 ⁻⁶ .K ⁻¹
Shore-D (DIN 53505) Shore-D	65 – 75
Deflection temperature °C	90 – 100

*measured average values

Standard dimensions:

- 1000 x 500 x 50 / 75 / 100 mm
- 1500 x 500 x 50 / 75 / 100 / 150 mm
- 2000 x 500 x 50 / 75 / 100 mm

Other dimensions, cuts, bonded blocks, rough pre-milling and block casts on request.

Boards, finished tools and models should be stored flat in dry conditions. The material should be acclimatized to 18 - 25° C prior to machining. Temperature variations should be kept as moderate as possible.

Status: May, 15th 2018