



obocastulan® 1850 blue

OBO-Werke GmbH

Am Bahnhof 5 · 31655 Stadthagen · Germany
Telefon (0 57 21) 78 01-0
Telefax (0 57 21) 7 78 55
www.obo-werke.de
info@obo-werke.de
USt-Id: DE171274404
St -Nr : 44/210/02193

Application

- laminating models
- galvano bath models

Properties

obocastulan® 1850 blue is individually manufactured and has the following properties:

- very fine surface structure
- high deflection temperature
- chemical resistance
- high abrasion resistance

The cast parts are completely unmachined.
The recommended offset for each surface is 10 mm.

Physical and Technical Data*

Colour	blue
Density kg/m ³ (approx.)	1840
Compressive strength MPa (DIN EN ISO 604)	130 – 135
Bending strength MPa (DIN EN ISO 178)	70 – 75
Linear thermal expansion co-efficient according to DIN 53752	$35 - 40 \times 10^{-6} \cdot K^{-1}$
Shore D (DIN 53505)	91 – 92
Heat resistance °C	115 - 120

* measured average values

During the experimental stage, the mechanical values may be subject to little change.

Dimensions:

- according to your specifications
- final contour casting according to CAD data
- available in large volumes

The technical data relating to the material and its processing has been compiled carefully and it's correct to the best of our knowledge. The information cannot, however, be taken to be legally binding nor as any commitment that the material has certain properties or is suited for any particular purpose.

Status: 06.06.2018